



<b>DATA SHEET</b>	Version	0
	Date	01/01/22
	Page	1 of 1

## PIVISTIK M/F

### First coat fluid polyurethane adhesive for leather and hides

#### CHARACTERISTICS

Solvent-based polychloroprene adhesive	METHOD	QUALITY CHARACTERISTICS (U.M.)
Appearance and Color	Visual	Clear
Viscosity	IO 07/42.10	100 – 200 cps
Specific weight	IO 07/42.3	0,840 – 0,860 g/cc
Dry content	IO 07/42.4	11 – 13%

#### USES

**Pivistik M/F** is a high fluidity polyurethane adhesive to be used exclusively as a first coat on absorbent materials. For best results it can be used with **Desmodur RFE** or **RC** at a rate of 2 – 5%.

#### INSTRUCTIONS FOR USE

Before use, mix the contents by repeatedly turning the container upside down. Apply the adhesive with a brush on previously roughened materials, 15-30 minutes after spreading, apply the second coat of polyurethane adhesive (e.g. **Pivistik B**). Supports coated with **Pivistik M/F** if kept free from dust or other impurities can be used for a second coat of polyurethane adhesive even after several days.

#### STORAGE

The product should be stored in the original packaging at room temperature (5-35°C). In these conditions it remains suitable for about 12 months.

Particularly low storage temperatures lead to a considerable reversible thickening of the product and, consequently, a more difficult distribution. Shake well before use.

#### PACKAGING

Metal containers Kg. net 5 - 15 - 25

#### NOTES

**Pivistik M/F** is highly flammable: make sure that the systems used for handling are correctly earthed to prevent the accumulation of electrostatic charges.