



<b>DATA SHEET</b>	Version	0
	Date	01/01/22
	Page	1 of 1

**NEOKITT**

## *Polychloroprene-based single-component adhesive*

### CHARACTERISTICS

Solvent-based polychloroprene adhesive	METHOD	QUALITY CHARACTERISTICS (U.M.)
Appearance and Color	Visual	Yellow Fluid
Viscosity	IO 07/42.10	2.400 - 2.700 cps
Specific Weight	IO 07/42.3	0,840 – 0,870 g/cc
Dry content	IO 07/42.4	19 - 21%
Time open	IO 07/42.6	15' – 30' at room temperature

### USES

**Neokitt** is a medium viscosity fast-setting adhesive specifically designed for the footwear and leather goods industry, to perform joining, hemming and bandaging operations quickly and effectively.

### INSTRUCTIONS FOR USE

Apply a uniform layer on both sides of **Neokitt** manually or with automatic systems, wait from 10 to 60 minutes, depending on the environmental conditions, then couple and press with adequate force, even manually.

**Neokitt** also lends itself to processes combined with products in aqueous dispersion with the same polychloroprene nature.

If you wish to check the adhesion strength with tensile tests, bear in mind that the definitive setting develops after at least 48 hours.

### STORAGE

The product should be stored in the original packaging at room temperature (5-35°C). In these conditions it remains suitable for about 12 months.

Particularly low storage temperatures lead to a considerable reversible thickening of the product and, consequently, a more difficult distribution. Shake well before use.

### PACKAGING

5 – 10 – 50 Kg Metallic Containers

### NOTES

**Neokitt** is highly flammable: make sure that the systems used for handling are properly earthed to avoid the accumulation of electrostatic charges.