



| | | |
|-------------------|---------|----------|
| DATA SHEET | Version | 0 |
| | Date | 01/01/22 |
| | Page | 1 of 1 |
| | | |

NEOSTIK SC Special Super

Adhesive for bonding foams

CHARACTERISTICS

| Synthetic rubber based adhesive | METHOD | QUALITY CHARACTERISTICS (U.M.) |
|---------------------------------|-------------|--------------------------------|
| Appearance and Color | Visual | Straw Yellow Fluid |
| Viscosity | IO 07/42.10 | 150 - 300 cps |
| Dry content | IO 07/42.4 | 39 - 41% |

USES

Neostik SC Special Super is suitable for bonding polyester and polyester-based polyurethane foams with themselves, wood, natural and synthetic fabrics, leather, metal, plastic, etc.

INSTRUCTIONS FOR USE

Spray with a gun with a 1.9 mm diameter nozzle at a pressure of 3-5 bar. Normal airless systems (under pressure) are also suitable for application.

Make sure that the materials to be glued are clean and dry, eliminating all traces of dust, dirt or other impurities from the surfaces. In the case of application from one side only, spray a large quantity of adhesive on one of the surfaces (couple immediately or in the shortest possible time and press uniformly).

In the case of an application on both sides, it is possible to couple the materials even after a time which, in some cases, can even reach 30 minutes.

Please Note: Bonding of plasticized PVC and its derivatives is not recommended, since, over time, the plasticizing oils contained in these products jeopardize the seal of the joint.

STORAGE

The product should be stored in the original packaging at room temperature (5-35°C). In these conditions it remains suitable for about 12 months.

Particularly low storage temperatures lead to a considerable reversible thickening of the product and, consequently, a more difficult distribution. Shake well before use.

PACKAGING

15 – 50 – 160 Kg Metallic Containers

NOTES

Neostik SC Special Super is highly flammable: make sure that the systems used for handling are properly earthed to avoid the accumulation of electrostatic charges.