



DATA SHEET	Version	0
	Date	01/01/22
	Page	1 of 1

PREPARATORE T

Elastomeric primer for polyurethane adhesives

CHARACTERISTICS

Solvent-based elastomeric primer	METHOD	QUALITY CHARACTERISTICS (U.M.)
Appearance and Color	Visual	Transparent Colorless
Dry content	IO 07/42.4	4 – 6%

USES

Preparatore T is used as a first coat on thermoformed EVA soles in combination with the subsequent use of a polyurethane adhesive.

INSTRUCTIONS FOR USE

The surfaces of the thermoformed EVA soles must be treated with a thin and uniform layer of **Preparatore T**. The application can be done with a brush. Leave to dry for approximately 30 minutes at room temperature, then apply the polyurethane adhesive which will be treated according to its procedures. It is very important that primed parts are treated with the adhesive within 3 - 4 days.

To further improve the final result, the application of the primer can be preceded by a wash with a particularly suitable product such as **Solvente EP**.

STORAGE

Preparatore T must be stored at temperatures between 5°C and 35°C in its original tightly closed containers, in a well-ventilated place and avoiding direct exposure to heat sources. The guaranteed stability in these conditions is 12 months.

PACKAGING

10 L Plastic Tank
1 L Plastic Bottle

NOTES

Preparatore T is highly flammable: make sure that the systems used for handling are correctly earthed to prevent the accumulation of electrostatic charges.