



| | | |
|-------------------|---------|----------|
| DATA SHEET | Version | 0 |
| | Date | 01/01/22 |
| | Page | 1 of 1 |
| | | |

SHOESTIK 500 T

Polychloroprene-based single-component adhesive

CHARACTERISTICS

| Solvent-based polychloroprene adhesive | METHOD | QUALITY CHARACTERISTICS (U.M.) |
|--|-------------|--------------------------------|
| Appearance and Color | Visual | Transparent fluid |
| Viscosity | IO 07/42.10 | 2300 – 2700 cps |
| Specific Weight | IO 07/42.3 | 0,840 – 0,870 g/cc |
| Dry content | IO 07/42.4 | 22 - 24% |
| Time open | IO 07/42.6 | 30' – 40' at room temperature |

USES

Shoestik 500/T is a medium viscosity quick-setting adhesive specifically designed for the footwear industry and specifically for splicing and binding operations.

INSTRUCTIONS FOR USE

Shoestik 500/T is suitable for use on materials such as leather, natural or synthetic, leather, cardboard and expanded materials.

Apply a uniform layer of product on both surfaces to be bonded, making sure they are free from dust or dirt. Wait up to a maximum of 2 hours, depending on the environmental conditions, press evenly. The adhesive develops the final grip after at least 48 hours.

STORAGE

The product should be stored in the original packaging at room temperature (5-35°C). In these conditions it remains suitable for about 12 months.

Particularly low storage temperatures lead to a considerable reversible thickening of the product and, consequently, a more difficult distribution. Shake well before use.

PACKAGING

5 – 15 – 25 Kg Metallic Containers

NOTES

Shoestik 500/T is highly flammable: make sure that the systems used for handling are correctly earthed to prevent the accumulation of electrostatic charges.