



<b>DATA SHEET</b>	Version	0
	Date	01/01/22
	Page	1 of 1

## SHOESTIK M/T

### Solvent-based polychloroprene adhesive in the footwear industry

#### CHARACTERISTICS

Solvent-based polychloroprene adhesive	METHOD	QUALITY CHARACTERISTICS (U.M.)
Appearance and Color	Visual	Yellow viscous liquid
Viscosity	IO 07/42.10	2900 – 3300 cps
Specific Weight	IO 07/42.3	0,840 – 0,870 g/cc
Dry content	IO 07/42.4	20 – 23%
Time open	IO 07/42.6	10' – 15'

#### USES

**Shoestik M/T** is suitable for gluing various materials such as: Leather, Wood and masonite, Natural and synthetic fabrics, non-woven fabrics, EVA, Leather and regenerated, Cardboard and cellulosic fibers

#### INSTRUCTIONS FOR USE

Apply, manually or with automatic systems, a uniform layer of **Shoestik M/T** on both surfaces to be glued free from traces of dust or grease: wait from 10 to 20 minutes (depending on the environmental conditions), then couple by applying careful pressure.

The dry product is odourless, flexible and light straw in colour. Bonding performed with **Shoestik M** has good mechanical and aging resistance. If you wish to check the adhesion strength with tensile tests, bear in mind that the definitive setting develops after at least 48 hours.

#### STORAGE

**Shoestik M/T** must be stored at temperatures between 5°C and 35°C in its original tightly closed containers, in a well-ventilated place and avoiding direct exposure to heat sources. The guaranteed stability in these conditions is 12 months.

Particularly low storage temperatures (especially in winter) lead to a considerable reversible thickening of the product and, consequently, a more difficult distribution. Mix well before use.

#### PACKAGING

15 – 25 – 50 Kg Metallic Containers

#### NOTES

**Attention!! Shoestik M/T is highly flammable:** make sure that the systems used for handling are correctly earthed to prevent the accumulation of electrostatic charges.